

# TECHNICAL SHEET

|                         |   |
|-------------------------|---|
| <b>BRAND</b>            | <b>CERAMICAS APARICI, S.A.</b><br>Ctra. Castellón - Alcora, km 12<br>12130 San Juan de Moró (Castellón) SPAIN   |
| <b>PRODUCT</b>          | <b>NAME: EVOKE BLUE, GREEN &amp; WHITE NATURAL</b><br><b>FORMAT (cm): 49,75 x 99,55</b>   |
| <b>TYPE OF PRODUCT</b>  | <b>TYPE:</b> Dry-pressed ceramic tiles, with water absorption<br>$E_b \leq 0,5\%$ <b>PORCELAIN TILE</b><br><b>USE:</b> For internal and external walls and floorings<br><b>GROUP BI<sub>a</sub></b> |
| <b>REFERENCED RULES</b> | <b>ISO-13006:2012 and UNE EN 14411:2013</b>   |

| Characteristics  | Test Method    | Requirements   | Values Compliance |
|--|----------------|--|-------------------|
| <b>A) DIMENSIONS AND SURFACE QUALITY</b>   |                |  |                   |
| <b>Length and width</b>  |                |  |                   |
| The work size shall be chosen as follows for:  |                |  |                   |
| a) modular tiles:  | EN ISO 10545-2 | In order to allow a nominal joint width of between 2 and 5 mm  | <b>PASS</b>       |
| b) non-modular tiles:  | EN ISO 10545-2 | So that the difference between the work size and the nominal size is not more than 2% (maximum 5 mm) | <b>PASS</b>       |
| The permissible deviation of the average size for each tile (2 or 4 sides) from the work size (W)<br>Requirements for nominal size N<br>$7\text{cm} \leq N < 15\text{cm}$<br>$N \geq 15\text{ cm}$ |                | $\pm 0,9\text{ mm}$<br>$\pm 2,0\text{ mm ó } \pm 0,6\%$  | <b>PASS</b>       |
| <b>Thickness</b>   |                |  |                   |
| a) The thickness shall be specified  |                | Declared thickness   | <b>SEE BOX</b>    |
| b) The permissible deviation, of the average thickness of each tile from the work size thickness<br>Requirements for nominal size N<br>$7\text{cm} \leq N < 15\text{cm}$<br>$N \geq 15\text{ cm}$  | EN ISO 10545-2 | $\pm 0,5\text{ mm}$<br>$\pm 0,5\text{ mm ó } \pm 5\%$  | <b>PASS</b>       |

|  |                |   |                    |
|--|----------------|---|--------------------|
| <b>Straightness of sides (facial sides)</b>  |                |   |                    |
| The maximum permissible deviation from straightness, related to the corresponding work sizes.<br>Requirements for nominal size N<br>$7\text{cm} \leq N < 15\text{cm}$<br>$N \geq 15\text{ cm}$                                   | EN ISO 10545-2 | $\pm 0,75\text{ mm}$<br>$\pm 1,5\text{ mm ó } \pm 0,5\%$  | <b>PASS</b>        |
| <b>Rectangularity</b>  |                |   |                    |
| The maximum permissible deviation from rectangularity, related to the corresponding work sizes.<br>Requirements for nominal size N<br>$7\text{cm} \leq N < 15\text{cm}$<br>$N \geq 15\text{ cm}$                                 | EN ISO 10545-2 | $\pm 0,75\text{ mm}$<br>$\pm 2,0\text{ mm ó } \pm 0,5\%$  | <b>PASS</b>        |
| <b>Surface flatness</b>  |                |   |                    |
| The maximum permissible deviation from flatness<br><br>a) centre curvature, related to diagonal calculated from the work sizes.<br>Requirements for nominal size N<br>$7\text{cm} \leq N < 15\text{cm}$<br>$N \geq 15\text{ cm}$ | EN ISO 10545-2 | $\pm 0,75\text{ mm}$<br>$\pm 2,0\text{ mm ó } \pm 0,5\%$  | <b>PASS</b>        |
| b) edge curvature, related to the corresponding work sizes.<br>Requirements for nominal size N<br>$7\text{cm} \leq N < 15\text{cm}$<br>$N \geq 15\text{ cm}$   | EN ISO 10545-2 | $\pm 0,75\text{ mm}$<br>$\pm 2,0\text{ mm ó } \pm 0,5\%$  | <b>PASS</b>        |
| c) warpage, related to diagonal calculated from the work sizes.<br>Requirements for nominal size N<br>$7\text{cm} \leq N < 15\text{cm}$<br>$N \geq 15\text{ cm}$   | EN ISO 10545-2 | $\pm 0,75\text{ mm}$<br>$\pm 2,0\text{ mm ó } \pm 0,5\%$  | <b>PASS</b>        |
| <b>Surface quality</b>   |                |   |                    |
|  | EN ISO 10545-2 | A minimum of 95% of the tiles shall be free from visible defects that would impair the appearance of a major area of tiles. | <b>PASS</b>        |
| <b>B) PHYSICAL PROPERTIES</b>  |                |   |                    |
| <b>Water absorption (in % by mass)</b>   |                |   |                    |
|  | EN ISO 10545-3 | $E_b \leq 0,5\%$<br><b>Individual maximum 0,6%</b>  | $E_b \leq 0,2\%$   |
| <b>Breaking strength, for:</b>   |                |   |                    |
| Thickness $\geq 7,5\text{ mm}$   | EN ISO 10545-4 | Not less than 1.300 N   | <b>&gt;2.500 N</b> |

|  |                                 |  |   |
|--|---------------------------------|--|---|
| <b>Flexural tensile strength or modulus of rupture</b>                                       |                                 |  |   |
|  | EN ISO 10545-4                  | Minimum 35 N/mm <sup>2</sup><br>Individual minimum<br>32 N/mm <sup>2</sup> | > 41 N/mm <sup>2</sup>                                  |
| <b>Coefficient of linear thermal expansion</b>   |                                 |  |   |
| from ambient temperature to 100° C   | EN ISO 10545-8                  | Declared<br>Value  | 6.1- 6.9 x10 <sup>-6</sup> (°C <sup>-1</sup> )          |
| <b>Abrasion resistance</b>   |                                 |  |   |
| Resistance to surface abrasion of<br><b>glazed tiles</b> intended for use on<br>floors (PEI) | EN ISO 10545-7                  | Abrasion class   | <b>BLUE CLASS 4<br/>GREEN CLASS 4<br/>WHITE CLASS 4</b> |
| <b>Thermal shock resistance</b>  |                                 |  |   |
|  | EN ISO 10545-9                  | Pass according to<br>EN ISO 10545-9  | <b>PASS</b>   |
| <b>Crazing resistance</b>  |                                 |  |   |
| Glazed tiles   | EN ISO 10545-11                 | Pass according to<br>EN ISO 10545-11                                       | <b>PASS</b>   |
| <b>Frost resistance</b>  |                                 |  |   |
| Interior uses  | EN ISO 10545-12                 | Pass according to<br>EN ISO 10545-12                                       | <b>PASS</b>   |
| Exterior uses  |                                 |  | <b>PASS</b>   |
| <b>Bond strength/adhesion , for:</b>   |                                 |  |   |
| cementitious adhesives   | EN 12004:2007 +A1:<br>2012, 4.1 | Declared<br>Value  | <b>Type C2<br/>&gt;1 N/mm<sup>2</sup></b>               |
| <b>Reaction to fire</b>  |                                 |  |   |
|  |                                 | Class A1 FL/A1   | <b>A1 FL/A1</b>   |
| <b>C) CHEMICAL PROPERTIES</b>  |                                 |  |   |
| <b>Resistance to chemicals</b>   |                                 |  |   |
| Resistance to household chemicals<br>and swimming pool slats                                 | EN ISO 10545-13                 | Minimum GB   | <b>GA</b>   |
| <b>Resistance to staining, for:</b>  |                                 |  |   |
| Glazed tiles   | EN ISO 10545-14                 | Minimum 3  | <b>5</b>  |