
















## Technical Data Sheet

SIZES		32 X 64 IN. Rectified Porcelain	
Body		Polished	Matte
Color / Finish			
			✓
6 Faces			

## Technical Specs.

### PORCELAIN

	Grout size	1/12"	
	P.E.I.	4 (Medium - Heavy Traffic)	
	Shade and Texture Mixture	High	
	Chemical Resistance	Compliant	A.S.T.M. C650
	DCOF	≥ 0.42	A.S.T.M. C1028
	Water absorption	≤ 0.5 %	A.S.T.M. C373
	MOHS	5 - 8	A.S.T.M. C1028
	Breaking Strength	≥ 771 lbs.	ISO 10545-4
	Thermal Shock Resistance	Compliant	A.S.T.M. C484
	Frost Resistance	Compliant	A.S.T.M. C1026
	Stain Resistance	Compliant	A.S.T.M. C1378
	Abrasion Resistance	Compliant	ANSI A137

## Packaging Information

SIZE	Pcs./Box	Sq.ft./Box	Lbs./Box	Box/PAL	Sq.ft./PAL	Lbs./PAL
32 X 64 IN.	2	27.55	131.5	24	661.20	3,217.4

Cesantoni certifies that the above results were obtained in laboratory testing performed by the quality control department.



## Ficha Técnica

FORMATOS		80 X 120 CM.	
Pasta		Porcelánico Rectificado	
Color / Acabado	Pulido	Mate	
		✓	
6 Faces			

## Información Técnica

### PORCELÁNICO

	Separación de boquilla	2 mm	
	P.E.I.	4 (Tráfico: - Alto)	
	Tono y Textura Mezclado	Alto	
	Resistencia al ataque químico	Conforme	A.S.T.M. C650
	Coefficiente Dinámico de Fricción	≥ 0.42	A.S.T.M. C1028
	Absorción de agua	≤ 0.5 %	A.S.T.M. C373
	MOHS	5 - 8	A.S.T.M. C1028
	Resistencia a la flexión	≥ 350 kg	ISO 10545-4
	Resistencia al shock térmico	Conforme	A.S.T.M. C484
	Resistencia a helada	Conforme	A.S.T.M. C1026
	Resistencia a las manchas	Conforme	A.S.T.M. C1378
	Resistencia a la abrasión	Conforme	ANSI A137

## Información de Embalaje

FORMATOS	Pzs./Caja	m2/Caja	Kg./Caja	Caja/Tarima	m2/Tarima	Kg./Tarima
80 X 160 CM	2	2.56	59.65	24	61.44	1,459.4