





























Technical Data Sheet

| SIZE Body | 9 X 10 IN. (Hex) Rectified Porcelain | Faces |
|--|--------------------------------------|---------|
| Color / Finish | Matte | |
|  | ✓ | 8 Faces |

| SIZE Body | 8 X 48 IN. Rectified Porcelain | Faces |
|--|--------------------------------|----------|
| Color / Finish | Matte | |
|  | ✓ | 20 Faces |

Technical Specs.

| PORCELAIN (9 x 10 IN.) | | | |
|--|---------------------------|----------------------------|------------------|
|  | Grout size | 1/12" | |
|  | P.E.I. | 4 (Medium - Heavy Traffic) | |
|  | Shade and Texture Mixture | High | |
|  | Chemical Resistance | Compliant | A.S.T.M. C650 |
|  | DCOF | ≥ 0.42 Interior Wet (IW) | ANSI A326.3-2021 |
|  | Water absorption | ≤ 0.5 % | A.S.T.M. C373 |
|  | MOHS | 5 - 8 | A.S.T.M. C1028 |
|  | Breaking Strength | ≥ 771 lbs. | ISO 10545-4 |
|  | Thermal Shock Resistance | Compliant | A.S.T.M. C484 |
|  | Frost Resistance | Compliant | A.S.T.M. C1026 |
|  | Stain Resistance | Compliant | A.S.T.M. C1378 |
|  | Abrasion Resistance | Compliant | ANSI A137 |

| PORCELAIN (8 x 48 IN.) | | | |
|---|---------------------------|----------------------------|--------------------|
|  | Grout size | 1/6" | |
|  | P.E.I. | 4 (Medium - Heavy Traffic) | |
|  | Shade and Texture Mixture | High | |
|  | Chemical Resistance | Compliant | A.S.T.M. C650 |
|  | DCOF | ≥ 0.42 Interior Wet (IW) | ANSI A326.3 - 2021 |
|  | Water absorption | ≤ 0.5 % | A.S.T.M. C373 |
|  | MOHS | 5 - 8 | A.S.T.M. C1028 |
|  | Breaking Strength | ≥ 771 lbs. | ISO 10545-4 |
|  | Thermal Shock Resistance | Compliant | A.S.T.M. C484 |
|  | Frost Resistance | Compliant | A.S.T.M. C1026 |
|  | Stain Resistance | Compliant | A.S.T.M. C1378 |
|  | Abrasion Resistance | Compliant | ANSI A137 |


Packaging Information


| SIZE | Pcs./Box | Sq.ft./Box | Lbs./Box | Box/PAL | Sq.ft./PAL | Lbs./PAL |
|------------|----------|------------|----------|---------|------------|----------|
| 9 X 10 IN. | 18 | 9.08 | 33.84 | 65 | 590.07 | 2,278.9 |
| 8 X 48 IN. | 7 | 18.09 | 88.01 | 24 | 434.16 | 2,157.9 |

Cesantoni certifies that the above results were obtained in laboratory testing performed by the quality control department.



Ficha Técnica

| FORMATO Cuerpo | 23.2 X 26.7 CM. (Hex) Porcelánico Rectificado | Caras |
|--|--|---------|
| Color / Acabado | Matte | |
|  | ✓ | 8 Caras |

| FORMATO Cuerpo | 20 x 120 CM. Rectified Porcelain | Caras |
|--|-------------------------------------|----------|
| Color / Acabado | Matte | |
|  | ✓ | 20 Caras |

Especificaciones Técnicas

PORCELÁNICO (23.2 x 26.7 CM)

| | | | |
|--|-----------------------------------|---------------------------|--------------------|
|  | Separación de boquilla | 4 mm | |
|  | P.E.I. | 4 (Tráfico: Medio - Alto) | |
|  | Tono y Textura Mezclado | Alto | |
|  | Resistencia al ataque químico | Conforme | A.S.T.M. C650 |
|  | Coefficiente Dinámico de Fricción | ≥ 0.42 Interior Húmedo | ANSI A326.3 - 2021 |
|  | Absorción de agua | ≤ 0.5 % | A.S.T.M. C373 |
|  | MOHS | 5 - 8 | A.S.T.M. C1028 |
|  | Resistencia a la flexión | ≥ 350 kg | ISO 10545-4 |
|  | Resistencia al shock térmico | Conforme | A.S.T.M. C484 |
|  | Resistencia a helada | Conforme | A.S.T.M. C1026 |
|  | Resistencia a las manchas | Conforme | A.S.T.M. C1378 |
|  | Resistencia a la abrasión | Conforme | ANSI A137 |

PORCELÁNICO (20 x 120 CM)

| | | | |
|---|-----------------------------------|---------------------------|--------------------|
|  | Separación de boquilla | 2 mm | |
|  | P.E.I. | 4 (Tráfico: Medio - Alto) | |
|  | Tono y Textura Mezclado | Alto | |
|  | Resistencia al ataque químico | Conforme | A.S.T.M. C650 |
|  | Coefficiente Dinámico de Fricción | ≥ 0.42 Interior Húmedo | ANSI A326.3 - 2021 |
|  | Absorción de agua | ≤ 0.5 % | A.S.T.M. C373 |
|  | MOHS | 5 - 8 | A.S.T.M. C1028 |
|  | Resistencia a la flexión | ≥ 350 kg | ISO 10545-4 |
|  | Resistencia al shock térmico | Conforme | A.S.T.M. C484 |
|  | Resistencia a helada | Conforme | A.S.T.M. C1026 |
|  | Resistencia a las manchas | Conforme | A.S.T.M. C1378 |
|  | Resistencia a la abrasión | Conforme | ANSI A137 |

Packaging Information

| FORMATO | Pzs./Caja | m2/Caja | Kg./Caja | Caja/Tarima | m2/Tarima | Kg./Tarima |
|----------------|-----------|---------|----------|-------------|-----------|------------|
| 23.2 X 26.7 CM | 18 | 0.84 | 15.50 | 65 | 54.6 | 1,033.7 |
| 20 X 120 CM | 7 | 1.68 | 39.95 | 24 | 40.32 | 978.8 |